

**General Description**

CRYLCOAT® 2693-3 is a tribo active Primid® polyester resin for use in matte dry blend systems to produce, in combination with CRYLCOAT® 2668-3, powder coatings with 60° gloss between 25 and 30 units.

(Formerly CRYLCOAT® E 04493)

Preliminary Technical Data Sheet

**Saturated Polyester Resin**

**Product Specification**

|                                      | Limits        |
|--------------------------------------|---------------|
| Appearance                           | Pale granules |
| Brookfield Viscosity @ 200 °C, mPa.s | Approx. 8000  |
| Color, b-value                       | Max. 15       |
| Acid value (mg KOH/g)                | Approx. 55    |

**Shelf Life**

Under normal storage conditions ( $\leq 30^{\circ}\text{C}$ ), the shelf life of the resin will be 24 months from date of manufacturing. For product older than 24 months, it is recommended to check the acid value and the viscosity every year.

**Safety & Environmental Protection**

For more information, please refer to the Material Safety Data Sheet.

July 2020 – Supersedes previous versions

**Other Properties**

|                       | Typical value |
|-----------------------|---------------|
| Glass transition (°C) | Approx. 60    |