

General Description

CRYLCOAT® 2693-6 is a low bake tribo active Primid® polyester resin for matte dry blend systems in a ratio of 93/7. In combination with CRYLCOAT® 2668-6 powder coatings with 60° gloss between 25 and 30 gloss units can be formulated. Full cure can be achieved at 12 min x 160°C schedule.

(Formerly CRYLCOAT® E 04693)

Preliminary Technical Data Sheet

Saturated Polyester Resin

Product Specification

	Limits
Appearance	Pale granules
Brookfield Viscosity @ 200 °C, mPa.s	Approx. 11000
Color, b-value	Max. 15
Acid value (mg KOH/g)	Approx. 54

Other Properties

	Typical value
Glass transition (°C)	Approx. 60

Starting Formulation

Component	Weight (%)	
CRYLCOAT® 2668-6	66.6	--
CRYLCOAT® 2693-6	--	63.9
Primid® XL 552	2.1	4.8
Titanium dioxide	30.0	30.0
MODAFLOW® Powder 6000	1.0	1.0
Benzoïn	0.3	0.3

Extrusion & Application Conditions

Extrusion	
Extruder	Twin screw
Speed	300 rpm
Torque	50 ± 5 %
Temperature	95 to 105 °C
Application	
Application	60 micrometer film on pre-treated Al panel
Spray Gun	Output voltage: 60 kV
Curing	12 min @ 160° C metal temperature

Film Properties

Test	Result
Gloss @ 60° (%) with CRYLCOAT® 2668-6 (1 : 1)	30
Reverse impact on Al (kg. cm or in lbs.)	50

Shelf Life

Under normal storage conditions (≤30°C), the shelf life of the resin will be 24 months from date of manufacturing. For product older than 24 months, it is recommended to check the acid value and the viscosity every year.

Safety & Environmental Protection

For more information, please refer to the Material Safety Data Sheet.

July 2020 – Supersedes previous versions