

General Description

SETAPOLL™ SP275 is a carboxyl functional polyester resin for Industrial outdoor durable, standard bake, corona applications when combined with β -hydroxyalkylamide at 93:7 ratio. This resin has very good overbake stability. Can also be used as part of a matte dry-blend system together with SETAPOLL™ SP271.

Saturated Polyester Resin

Product Specification

	Limits
Appearance	Pale Granules
Acid value (mg KOH/g)	46-52
Brookfield Viscosity @ 200 °C, mPa.s	2500-4500
Color, b value	Max. 15

Other Properties

	Typical value
Glass transition (°C)	Approx. 60

Application Conditions

Application	
Application	60 micrometer film on 0.6 mm aluminium panel
Curing	10 min @ 180 °C peak metal temperature

Shelf Life

Under normal storage conditions ($\leq 30^{\circ}\text{C}$), the shelf life of the resin will be 24 months from date of manufacturing. For product older than 24 months, it is recommended to check the acid value and the viscosity every year.

Safety & Environmental Protection

For more information, please refer to the Material Safety Data Sheet.