

General Description

UVECOAT® 9539 is an amorphous unsaturated polyester resin for use in combination with other UVECOAT® resins to provide excellent adhesion of UV curable powder to a wide variety of metal substrates.

Unsaturated UV Curable Polyester Resin

Product Specification

	Limits
Appearance	Pale granules
Brookfield Viscosity @ 200 °C, mPa.s	2000-5000
Color, b-value	Max. 20
Acid value (mg KOH/g)	10-16

Other Properties

	Typical value
Glass transition (°C)	Approx. 44

Starting Formulation

Component	Weight (%)
UVECOAT® 9539	18.7
UVECOAT® 2100	56.3
Photoinitiators	2.5
Titanium dioxide	25.0
MODAFLOW® Powder 6000	1.0
Degassing Agent	0.5

Extrusion & Application Conditions

Extrusion	
Extruder	Twin screw
Speed	250 rpm
Torque	70 ± 5 %
Temperature	95 to 105 °C
Application	
Application	60 micrometer film on steel panel
Spray Gun	Output voltage: 60 kV Belt speed: 0.5-5 m/min
IR-UV oven	IR: 32 KW/m ² UV: 80-160 W/cm

Film Properties

Test	Result
Adhesion (Gt)	0
Reverse Impact (kg. cm. or in. lbs.)	160

Shelf Life

Under normal storage conditions (≤25°C), the shelf life of the resin will be 12 months from date of manufacturing. For product older than 12 months, it is recommended to check the acid value and the viscosity every year.

Safety & Environmental Protection

For more information, please refer to the Material Safety Data Sheet.

October 2021 – Supersedes previous versions