

General Description

CRYLCOAT® 4693-2 is a superdurable resin for use with Primid® XL-552 in the production of one-shot matte coatings. When used in combination with CRYLCOAT® 4651-0, powder coatings can achieve a 60° gloss between 5 and 12% while exhibiting good flow and outdoor durability.

(Formerly CRYLCOAT® E 04193)

Saturated Superdurable Polyester Resin

Product Specification

	Limits
Appearance	Pale granules
Brookfield Viscosity @ 200 °C, mPa.s	1500 - 2500
Color, b-value	Max. 20
Acid value (mg KOH/g)	80 - 95

Other Properties

	Typical value
Glass transition (°C)	Approx. 55

Starting Formulation

Component	Weight (%)
CRYLCOAT® 4693-2	37.2
CRYLCOAT® 4651-0	37.2
Primid® XL 552	6.0
Barium sulfate	14.8
Pigment RAL 8014	3.5
MODAFLOW® Powder 6000	1.0
Benzoin	0.3

Extrusion & Application Conditions

Extrusion	
Extruder	Twin screw
Speed	300 rpm
Torque	70 to 80 %
Temperature	85 to 100 °C
Application	
Application	60 micrometer film on 0.5 steel panel
Spray Gun	Output voltage: 60 kV
Curing	10 min @ 200 °C metal temperature

Film Properties

Test	Result
Gloss @ 60° (%)	5-12

Shelf Life

Under normal storage conditions ($\leq 30^{\circ}\text{C}$), the shelf life of the resin will be 24 months from date of manufacturing. For product older than 24 months, it is recommended to check the acid value and the viscosity every year.

Safety & Environmental Protection

For more information, please refer to the Material Safety Data Sheet.

July 2020 – Supersedes previous versions